

C0603C180J3HACAUTO

SMD Auto X8R HT150C, Ceramic, 18 pF, 5%, 25 VDC, X8R, SMD, MLCC, High Temperature, Ultra-Stable, Automotive Grade, 0603, 0.5 mm



General Information		
Series	SMD Auto X8R HT150C	
Style	SMD Chip	
Description	SMD, MLCC, High Temperature, Ultra-Stable, Automotive Grade	
Features	High Temperature, Ultra-Stable, Automotive Grade	
RoHS	Yes	
Termination	Tin	
Marking	No	
Qualifications	AEC-Q200	
AEC-Q200	Yes	
Typical Component Weight	4.8 mg	
Shelf Life	78 Weeks	
MSL	1	

Dimensions	
Chip Size	0603
L	1.6mm +/-0.15mm
W	0.8mm +/-0.15mm
Т	0.8mm +/-0.07mm
S	0.5mm MIN
В	0.35mm +/-0.15mm

Т	0.8mm +/-0.07mm	
S	0.5mm MIN	
В	0.35mm +/-0.15mm	
Packaging Specifications		

Specifications		
Capacitance	18 pF	
Measurement Condition	1 MHz 1.0Vrms	
Tolerance	5%	
Voltage DC	25 VDC	
Dielectric Withstanding Voltage	62.5 VDC	
Temperature Range	-55/+150°C	
Temp. Coefficient	X8R	
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	15%, 1MegaHz 1.0Vrms	
Dissipation Factor	2.5% 1 MHz 1.0Vrms	
Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours	
Insulation Resistance	100 GOhms	

Packaging Specifications		Capacitance Change with	15%, 1MegaHz 1.0Vrms
Packaging	T&R, 180mm, Paper Tape	Reference to +25°C and 0 VDC Applied (TCC)	1570, IMEGANZ 1.0 VIIIIS
Packaging Quantity 4000	4000	Dissipation Factor	2.5% 1 MHz 1.0 Vrms
		Aging Rate	0% Loss/Decade Hour: Referee Time is 1000 Hours
		Insulation Resistance	100 GOhms

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 06/12/2025 © 2006 - 2025 YAGEO