




Aliases (SM24B104K202) KPS SM SMD Indust X7R HV, Ceramic, 0.1 uF, 10%, 2,000 VDC, X7R, SM24



| Click here for the 3D mode | .اد |
|----------------------------|-----|
|----------------------------|-----|

| Dimensions | |
|------------|--------------------|
| L | 11.43mm +/-0.762mm |
| W | 10.16mm +/-0.762mm |
| Т | 5.588mm MAX |
| A | 7.62mm MAX |
| В | 2.54mm +/-0.508mm |

| Packaging Specifications | | |
|--------------------------|------|--|
| Packaging | Tray | |
| Packaging Quantity | 50 | |

| General Information | |
|---------------------|---|
| Series | KPS SM SMD Indust X7R HV |
| Style | Stacked Chip |
| Description | SMD, Fixed, High Volt, Low ESR, Leaded, Industrial |
| Features | High Voltage, Low ESR, Industrial Grade |
| RoHS | With Exemptions |
| REACH | SVHC (Pb - CAS 7439-92-1) |
| Termination | Silver |
| AEC-Q200 | No |
| Chip Size | SM24 |
| Shelf Life | 78 Weeks |
| MSL | 1 |

| Specifications | |
|--|---------------------|
| Capacitance | 0.1 uF |
| Measurement Condition | 1 kHz 1.0Vrms |
| Tolerance | 10% |
| Voltage DC | 2000 VDC |
| Dielectric Withstanding Voltage | 2,400 VDC |
| Temperature Range | -55/+125°C |
| Temp. Coefficient | X7R |
| Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC) | 15%, 1kHz 1.0Vrms |
| Dissipation Factor | 2.5%1kHz1.0Vrms |
| Aging Rate | 3% Loss/Decade Hour |
| Insulation Resistance | 10 GOhms |

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 05/24/2025 © 2006 - 2025 YAGEO