
## T322A474K025AT









|            | ı                            |  |
|------------|------------------------------|--|
|            | Click here for the 3D model. |  |
| Dimensions |                              |  |
| D          | 2.41mm MAX                   |  |
| L          | 6.6mm MAX                    |  |
| LL         | 25.4mm MIN                   |  |
| F          | 0.51mm +/-0.05mm             |  |

| Packaging Specifications |           |
|--------------------------|-----------|
| Packaging                | Bulk, Bag |
| Packaging Quantity       | 300       |

| General Information |  |
|---------------------|--|
| Series              | T322   |
| Dielectric          | MnO2 Tantalum  |
| Style               | Axial  |
| Description         | Axial, Solid Tantalum, Molded,<br>Military (Non-ER), Low ESR |
| Features            | Low ESR  |
| RoHS                | Yes  |
| Termination         | Tin  |
| Lead                | Wire Leads   |
| AEC-Q200            | No   |
| Notes               | Uninsulated.   |
| Shelf Life          | 156 Weeks  |

| Specifications     |   |
|--------------------|---|
| Capacitance        | 0.47 uF   |
| Tolerance          | 10%   |
| Voltage DC         | 25 VDC (85C), 16.68 VDC (125C<br>Surge), 0.25 VDC (125C<br>Reverse) |
| Temperature Range  | -55/+125°C  |
| Rated Temperature  | 85°C  |
| Dissipation Factor | 3%  |
| Leakage Current    | 0.5 uA (25°C)   |

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 12/04/2025 © 2006 - 2025 YAGEO