

T489D106K035ATA400

General Information

T489 Auto, Tantalum, MnO2 Tantalum, Commercial Grade, 10 uF, 10%, 35 VDC, SMD, MnO2, Molded, Low Leakage, Auto, AEC-Q200, 400 mOhms, 7343, 3.1 mm, 1.3 mm


CATHODE (-) END VIEW



ANODE (+) END VIEW

SIDE VIEW





Click here for the 3D model.

| Series | T489 Auto |
|--------------------------|---|
| Dielectric | MnO2 Tantalum |
| Style | SMD Chip |
| Description | SMD, MnO2, Molded, Low Leakage, Auto, AEC-Q200 |
| Features | Low Leakage, Automotive |
| RoHS | Yes |
| Termination | Tin |
| Qualifications | AEC-Q200 |
| AEC-Q200 | Yes |
| Typical Component Weight | 446.844 mg |

| Specifications | |
|--------------------|-----------------------------------|
| Capacitance | 10 uF |
| Tolerance | 10% |
| Voltage DC | 35 VDC (85C), 23.45 VDC (125C) |
| Temperature Range | -55/+125°C |
| Rated Temperature | 85°C |
| Dissipation Factor | 6% 120Hz 25C |
| Failure Rate | N/A |
| ESR | 400 mOhms (100kHz 25C) |
| Ripple Current | 612 mA (rms, 100kHz 25C) |
| Leakage Current | 2.6 uA (5min 25°C) |

| Dimensions | |
|------------|--------------------|
| L | 7.3mm +/-0.3mm |
| W | 4.3mm +/-0.3mm |
| н | 2.8mm +/-0.3mm |
| т | 0.13mm REF |
| S | 1.3mm +/-0.3mm |
| F | 2.4mm +/-0.1mm |
| A | 3.8mm MIN |
| В | 0.5mm +/-0.15mm |
| E | 3.5mm REF |
| G | 3.5mm REF |
| Р | 0.9mm REF |
| R | 1mm REF |
| х | 0.1mm +/-0.1mm REF |

| Packaging Specifications | |
|--------------------------|------------|
| Packaging | T&R, 178mm |
| Packaging Quantity | 500 |

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.