


T497H156K025BH6411

T497 HRA, Tantalum, MnO2 Tantalum, HRA, 15 uF, 10%, 25 VDC, SMD, MnO2, Molded, High Reliability, Medical, B (0.1%/1000 Hrs), 1 Ohms, 7238, 3.17 mm, 1.27 mm



| General Information | |
|--------------------------|---|
| Series | T497 HRA |
| Dielectric | MnO2 Tantalum |
| Style | SMD Chip |
| Description | SMD, MnO2, Molded, High Reliability, Medical |
| Features | High Reliability, Medical |
| RoHS | No |
| Prop 65 | WARNING: Cancer and reproductive harm - https://www.p65warnings.ca.gov / |
| SCIP Number | 1dd2e1b8-26dd-4d52-927c-6f9 d519011aa |
| Termination | Tin Lead (SnPb) |
| Qualifications | CWR09/19/29 Style |
| AEC-Q200 | No |
| Typical Component Weight | 349.01 mg |
| Miscellaneous | F1Technology + Simulated Breakdown Screening (SBDS). |
| Notes | Note: When solder coated terminations are required, add an additional 0.38mm (0.015inch) to the tolerances for "L", "W", "H", "K", "F" and "S". |
| MSL | 1 |

| 7.24mm +/-0.38mm |
|----------------------|
| 3.81mm +/-0.38mm |
| 2.79mm +/-0.38mm |
| 1.27mm +0.25/-0.13mm |
| 3.68mm +0.13/-0.51mm |
| 1.52mm MIN |
| 0.76mm MIN |
| |
| |
| T&R, 178mm |
| 500 |
| |

| - · · · · · | |
|-------------------------|---|
| Specifications | |
| Capacitance | 15 uF |
| Tolerance | 10% |
| Voltage DC | 25 VDC (85C), 16.75 VDC (125C) |
| Temperature Range | -55/+125°C |
| Rated Temperature | 85°C |
| Humidity | 85C, 85% RH, 1000 Hours, No Load |
| Dissipation Factor | 6% 120Hz 25C |
| Failure Rate | B (0.1%/1000 Hrs) |
| ESR | 1 Ohms (100kHz 25C) |
| Ripple Current | 387 mA (rms, 100kHz 25C) |
| Leakage Current | 3.8 uA (5min 25°C) |
| Testing and Reliability | 10 Cycles Surge Current Testing At -55C And +85C |

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

Generated 07/04/2025 © 2006 - 2025 YAGEO